


Intended use


Mipa Haftgrund is a fast drying 1K steel primer. For interior and exterior use and recoatable with all Mipa KH paints based on synthetic resin.

Colours: H 624 red-brown , H 629 grey. Further colour shades on request.


Processing instructions


	Mixing ratio		
	hardener	by weight (lacquer : hardener)	by volume (lacquer : hardener)
	--	--	--


	Hardener	--
---	-----------------	----

	Pot life	with Härterverdünnung 2 days
---	-----------------	------------------------------

	Thinner	Mipa UN-Verdünnung Mipa Verdünnung UN 21 Mipa Härterverdünnung
--	----------------	--

	Processing viscosity	
	gravity spray gun	Airmix/Airless
	20 - 25 s 4 mm DIN	40 - 50 s 4 mm DIN

	Application mode					
	application mode	hardener	pressure (bar)	nozzle (mm)	spray passes	dilution
	gravity spray gun/ HVLP	--	2,0 - 2,5	1,3 - 1,8	2 - 3	15 - 20 %
	Airmix / Airless compound pressure	--	1,0 - 2,0 100 - 120	0,28 - 0,33	1 - 2	5 - 10 %
	brush, roller	--	--	--	--	0 - 5 %

	Drying time						
	hardener	object temperature	dust dry	set to touch	ready for assembly	sandable	recoatable
	--	20 °C	10 - 20 min	30 - 60 min	--	--	1 - 2 h (1 h for 1K paints, 2 h for 2K paints)
	--	60 °C	--	--	30 min	--	--

Fully cured after 3 - 4 days (at 20 °C).

Note

Characteristics:

binder base:	alkyd resin
solids content (% by weight):	~ 76
solids content (% by volume):	~ 54
delivery viscosity DIN 53211 4 mm (in s):	70 - 90
density DIN EN ISO 2811 (kg/l):	~ 1,8
gloss level ISO 2813 at 60° (GU):	< 20 matt

Properties:

good flow, fast drying
active corrosion protection (zinc phosphate)
electrostatic application is possible when adding approx. 10 % of thinner Verdünnung UN
very good weather resistance
adhesive, shock and scratch-resistant
resistant to cleaning agents and in case of temporary exposure also to oils, greases, fuels, acids and alkali in low concentration
resistance to heat: - short-term heat exposure: 150 °C
- permanent heat exposure: 120 °C
adhesion to steel

Theoretical spreading rate : ~ 35,2 m²/kg for 10 µm dry film thickness
~ 55,3 m²/l for 10 µm dry film thickness

Storage: For at least 3 years in the unopened original container. Optimum storage conditions between + 5 °C and + 25 °C, avoid direct sunlight. Other storage conditions may lead to undesirable properties of the material.

VOC: < 430 g/l.

Processing conditions: From + 10 °C and up to 80 % relative humidity. Ensure adequate air ventilation.

Substrate preparation: Remove oil, grease, rust, mill scale, rolling skins, as well as other substances impairing the function of the coating!

Attention: A direct adhesion cannot be taken as granted due to most different kinds of metals, alloys, metallic and conversion coatings and so on. The adhesion must therefore be tested on the original metal substrate.

steel:
- blast to cleaning degree Sa 2½, remove blast residues and overcoat promptly
- de-rust with hand and power tools to degree of cleanliness St 3
- degrease with Mipa WBS Reiniger or Mipa Silikonentferner

Proposed coating structure: steel:
priming coat: Haftgrund with 30 - 40 µm dry film thickness
finishing coat: *AK 200 / AK 240 / AK 250 with 50 - 60 µm dry film thickness

Special notes:

*Further Mipa topcoats are available. Please contact your technical adviser or our application technicians.

For professional use only.

The details of the paragraphs - Proposed coating structure, Characteristics, Theoretical spreading rate, VOC - refer to the colour shade H 629 grey. For other colour shades, these may deviate.

Do not overcoat with high-solid Mipa 2K topcoats.

Without top coating, the primed objects can be stored outside for approx. 5 days.

Cleaning of tools:

Clean tools immediately after use with Mipa Nitroverdünnung.