

### Intended use









1K filler to fill micropores by wiping the product on the surface, particularly of plastic.

Application mode:

Rub Mipa Porenwischfiller over the porous surface in a circular motion using a dry, clean and lint-free cloth pad. After drying (approx. 5-10 minutes at 20°C) remove any surplus material with a cloth moistened either with Mipa Kunststoffreiniger or Mipa Silikonentferner.

Spreading rate: --

### Processing instructions

	<b>Colour</b> dark grey					
	<b>Mixing ratio</b> <b>Hardener</b>		<b>by weight (lacquer : hardener)</b>	<b>by volume (lacquer : hardener)</b>		
	--	--	--	--		
	<b>Hardener</b> <b>for complete paintwork</b>			<b>for partial paintwork</b>		
	--			--		
	<b>Pot life</b>					
	--					
	<b>Thinner</b>					
	--					
	<b>Spray viscosity</b> ready for use <b>gravity spray gun</b>			<b>Airmix/Airless</b>		
	--			--		
	<b>Application mode</b> <b>Application mode</b>	<b>Hardener</b>	<b>pressure (bar)</b>	<b>nozzle (mm)</b>	<b>spray passes</b>	<b>Thinner</b>
	--	--	--	--	--	--
	<b>Flash-off time</b> 5 - 10 min					
	<b>Dry coat thickness</b>					
	--					



### Drying time

object temperature	dust dry	set to touch	ready for assembly	sandable	recoatable
20 °C	--	--	--	--	30 min
60 °C	--	--	--	--	10 min

### Note

**Storage:** at least 1 year in unopened original container

**VOC Regulation :** --

**Processing conditions:** from +10° C and up to 80 % relative air humidity. Ensure an adequate supply and exhaust air ventilation.

**Processing instructions:** The substrate must be clean, dry and free from grease. To be used only to fill micropores. Fill deep holes with Mipa polyester-based body fillers . Cleaning with Mipa Silikonentferner or Mipa Kunststoffreiniger is possible after 30 minutes after application.