


Intended use


Mipalin Kunstharz-Decklack is especially designed for complete and partial coatings of agricultural machinery, agricultural equipment and machinery in general.

Colours: Ready-mixed colours as per Colour-index and special colours.


Processing instructions


	Mixing ratio		
	hardener	by weight (lacquer : hardener)	by volume (lacquer : hardener)
	–	–	–

	Hardener	–
---	-----------------	---

	Pot life	2 days with Härterverdünnung
---	-----------------	------------------------------

	Thinner	Mipa UN-Verdünnung Mipa Verdünnung UN 21 Mipa Härterverdünnung
--	----------------	--

	Processing viscosity	
	gravity spray gun	Airmix/Airless
	18 - 22 s 4 mm DIN	40 - 50 s 4 mm DIN

	Application mode					
	application mode	hardener	pressure (bar)	nozzle (mm)	spray passes	dilution
	gravity spray gun/ HVLP	–	2,0 - 2,5	1,2 - 1,5	2 - 3	10 - 20 %
	Airmix / Airless compound pressure	–	1,0 - 2,0 100 - 120	0,23 - 0,28	2	10 %
	brush, roller	–	–	–	–	0 - 5 %

	Drying time						
	hardener	object temperature	dust dry	set to touch	ready for assembly	sandable	recoatable
	–	20 °C	30 - 60 min	6 - 8 h	24 h	–	–

Heat drying possible up to 80° C; before drying at higher temperatur allow flash-off of 10 - 15 minutes

Note

Characteristics:	binder base:	modified alkyd resin
	solids content (% by weight):	~ 55
	solids content (% by volume):	~ 47
	delivery viscosity DIN 53211 4 mm (in s):	120 - 130
	density DIN EN ISO 2811 (kg/l):	~ 1,2
	gloss level ISO 2813 at 60° (GU):	> 80 glossy

Properties:	short drying time
	good hiding power
	highly UV- and weather-resistant
	high vertical stability
	excellent flow, high final hardness, retains the gloss over time
	resistant to fuels and diesel if exposed temporarily
	heat resistance:
	- short-term heat exposure: 150°C
	- permanent heat exposure: 130°C

Theoretical spreading rate : ~ 46,6 m²/kg for 10 µm dry film thickness
~ 47,8 m²/l for 10 µm dry film thickness

Storage: For at least 3 years in the unopened original container. Optimum storage conditions between + 5 °C and + 25 °C, avoid direct sunlight. Other storage conditions may lead to undesirable properties of the material.

VOC: < 490 g/l.

Processing conditions: From + 10 °C and up to 80 % relative humidity. Ensure adequate air ventilation.

Substrate preparation: Remove oil, grease, rust, mill scale, rolling skins, as well as other substances impairing the function of the coating!

Attention: A direct adhesion cannot be taken as granted due to most different kinds of metals, alloys, metallic and conversion coatings and so on. The adhesion must therefore be tested on the original metal substrate.

steel:

- blast to cleaning degree Sa 2½, remove blast residues and overcoat promptly
- de-rust with hand and power tools to degree of cleanliness St 3
- degrease with Mipa WBS Reiniger or Mipa Silikonentferner

zincd substrates:

- clean the surface with the ammonia solution Mipa Zinkreiniger
- sweep blast

aluminium:

- degrease with Mipa 2K-Verdünnung, sand thoroughly with sandpaper P 360/400 and clean subsequently with Mipa Silikonentferner

wood (wood moisture max. 15 %):

- pre-sand with grit P 180 –P 280 and remove dust thoroughly

Proposed coating structure: steel:
priming coat: *AK 100-20 / AK 105-20 with 50 - 60 µm dry film thickness
finishing coat: Mipalin Kunstharz-Decklack with 50 - 60 µm dry film thickness

zincd substrates, aluminium:
priming coat: *VB 100-20 with 15 - 30 µm dry film thickness
finishing coat: Mipalin Kunstharz-Decklack with 50 - 60 µm dry film thickness

wood in exterior use:
impregnation: Mipaxyl spezial
priming coat: Mipa Malervorlack HS with 50 - 60 µm dry film thickness
finishing coat: Mipalin Kunstharz-Decklack with 50 - 60 µm dry film thickness

wood in interior use:
priming coat: Mipa Malervorlack HS with 50 - 60 µm dry film thickness
finishing coat: Mipalin Kunstharz-Decklack with 50 - 60 µm dry film thickness

Special notes: *Further Mipa primer are available. Please contact your technical adviser or our application technicians.

For professional use only.

The details of the paragraphs - Proposed coating structure, Characteristics, Theoretical spreading rate, VOC - refer to the colour shade RAL 7035. For other colour shades, these may deviate.

Applying too thick layers may extend considerably the drying time.

Depending on the colour, the delivery viscosity may vary. Adjust the viscosity by adding thinner.

Check colour before use.

Cleaning of tools: Clean tools immediately after use with Mipa Nitroverdünnung.