








Intended use

Fast drying special paint based on plastic reinforced synthetic resins that is particularly resistant to saltwater and humidity.

Colours: DB 7350 novagrau SG, RAL 9005 black GL, RAL 9011 MAN graphite-black SG. Further colour shades on request.

Processing instructions

| | | | | | | | |
|---|---------------------------------------|---------------------------|---------------------------------------|---------------------------------------|---------------------------|-----------------|-------------------|
|  | Mixing ratio | | | | | | |
| | hardener | | by weight (lacquer : hardener) | by volume (lacquer : hardener) | | | |
| | – | | – | – | | | |
|  | Hardener | | | | | | |
| | – | | | | | | |
|  | Pot life | | | | | | |
| | 2 days with Härterverdünnung | | | | | | |
|  | Thinner | | | | | | |
| | Mipa UN-Verdünnung | | | | | | |
| | Mipa Verdünnung UN 21 | | | | | | |
| | Mipa Härterverdünnung | | | | | | |
|  | Processing viscosity | | | | | | |
| | gravity spray gun | | | Airmix/Airless | | | |
| | 18 - 22 s 4 mm DIN | | | 40 - 60 s 4 mm DIN | | | |
|  | Application mode | | | | | | |
| | application mode | hardener | pressure (bar) | nozzle (mm) | spray passes | dilution | |
| | gravity spray gun/ HVLP | – | 2,0 - 2,5 | 1,2 - 1,5 | 2 - 3 | 15 - 20 % | |
| | Airmix / Airless compound pressure | – | 1,0 - 2,0 100 - 120 | 0,23 - 0,28 | 2 | 10 % | |
|  | Drying time | | | | | | |
| | hardener | object temperature | dust dry | set to touch | ready for assembly | sandable | recoatable |
| | – | 20 °C | 30 - 60 min | 5 - 6 h | 16 h | – | – |
| | – | 60 °C | 10 - 15 min | 40 - 60 min | after cooling | – | – |

Before drying at higher temperature, allow flash-off of 10 - 15 minutes

Note

| | | |
|-------------------------|---|-----------------------|
| Characteristics: | binder base: | modified alkyd resins |
| | solids content (% by weight): | ~ 55 |
| | solids content (% by volume): | ~ 47 |
| | delivery viscosity DIN 53211 4 mm (in s): | 100 - 120 |
| | density DIN EN ISO 2811 (kg/l): | ~ 1,2 |
| | gloss level ISO 2813 at 60° (GU): | depends on the colour |

| | |
|--------------------|--|
| Properties: | short drying time |
| | good hiding power |
| | highly UV- and weather-resistant |
| | excellent vertical stability |
| | excellent flow, high final hardness, stable gloss |
| | resistant to fuels and diesel if exposed temporarily |
| | particularly resistant to saltwater and humidity |
| | heat resistance: |
| | - short-term heat exposure: 150 °C |
| | - permanent heat exposure: 130 °C |

Theoretical spreading rate : ~ 45,2 m²/kg for 10 µm dry film thickness
~ 46,4 m²/l for 10 µm dry film thickness

Storage: For at least 3 years in the unopened original container. Optimum storage conditions between + 5 °C and + 25 °C, avoid direct sunlight. Other storage conditions may lead to undesirable properties of the material.

VOC: < 500 g/l.

Processing conditions: From + 10 °C and up to 80 % relative humidity. Ensure adequate air ventilation.

Substrate preparation: Remove oil, grease, rust, mill scale, rolling skins, as well as other substances impairing the function of the coating!

Attention: A direct adhesion cannot be taken as granted due to most different kinds of metals, alloys, metallic and conversion coatings and so on. The adhesion must therefore be tested on the original metal substrate.

steel:

- blast to cleaning degree Sa 2½, remove blast residues and overcoat promptly
- de-rust with hand and power tools to degree of cleanliness St 3
- degrease with Mipa WBS Reiniger or Mipa Silikonentferner

Proposed coating structure: steel:
priming coat: *AK 100-20 / AK 105-20 with 50 - 60 µm dry film thickness
finishing coat: Mipalin FG-Spezial-Chassislack with 50 - 60 µm dry film thickness

Special notes:

*Further Mipa primers are available. Please contact your technical adviser or our application technicians.

For professional use only.

The details of the paragraphs - Proposed coating structure, Characteristics, Theoretical spreading rate, VOC - refer to the colour shade DB 7350 novagrau SG. For other colour shades, these may deviate.

Applying too thick layers may extend considerably the drying time.

Depending on the colour, the delivery viscosity may vary. Adjust the viscosity by adding thinner.

Check colour before use.

Cleaning of tools:

Clean tools immediately after use with Mipa Nitroverdünnung.