


Intended use

This waterborne 1K zinc phosphate primer for steel substrates can be applied by paint brush, roller and spraying. Recoatable with all solvent- and waterborne 1K and 2K paints.

Processing instructions**Mixing ratio****hardener**

--

by weight (lacquer : hardener)

--

by volume (lacquer : hardener)

--

**Hardener**


--

**Pot life**

--

**Thinner**

Mipa WBS VE-Wasser

**Processing viscosity****gravity spray gun**

30 - 40 s 4 mm DIN

Airmix/Airless

50 - 60 s 4 mm DIN

**Application mode****application mode****hardener****pressure
(bar)****nozzle (mm)****spray
passes****dilution**gravity spray gun/
HVLP

--

2,0 - 2,2

1,5 - 1,8

2 - 3

2 - 7 %

Airmix / Airless
compound pressure

--

1,0 - 2,0
100 - 120

0,23 - 0,33

1 - 2

0 - 2 %

Streichen, Rollen

--

--

--

--

0 %

**Drying time****hardener****object
temperature****dust dry****set to
touch****ready for
assembly****sandable****recoatable**

--

20 °C

15 - 25 min

25 - 35 min

24 h

--

1 - 2 h (1 h for
waterborne
paints, 2 h for
solventborne
paints)

--

60 °C

--

5 - 7 min

45 min

--

25 min

Note

Characteristics:	binder base: styrene acrylic copolymer solids content (% by weight): ~ 50 solids content (% by volume): ~ 37 delivery viscosity DIN 53211 4 mm (in s): 80 - 100 density DIN EN ISO 2811 (kg/l): ~ 1,3 gloss level ISO 2813 at 60° (GU): 10 - 20 matt
Properties:	short drying times corrosion protection high tolerance of grease and oil heat resistance: - short-term heat exposure: 120 °C - permanent heat exposure: 80 °C adhesion to steel
Theoretical spreading rate:	~ 29,2 m²/kg for 10 µm dry film thickness ~ 34,0 m²/l for 10 µm dry film thickness
Storage:	For at least 2 years in the unopened original container. Optimum storage conditions between + 5 °C and + 25 °C, avoid direct sunlight. Other storage conditions may lead to undesirable properties of the material.
VOC:	< 70 g/l.
Processing conditions:	From + 10 °C and up to 70 % relative humidity. Ensure adequate air ventilation.
Substrate preparation:	Remove oil, grease, rust, mill scale, rolling skins, as well as other substances impairing the function of the coating! Attention: A direct adhesion cannot be taken as granted due to most different kinds of metals, alloys, metallic and conversion coatings and so on. The adhesion must therefore be tested on the original metal substrate. steel: - blast to cleaning degree Sa 2½, remove blast residues and overcoat promptly - de-rust with hand and power tools to degree of cleanliness St 3 - degrease with Mipa WBS Reiniger or Mipa Silikonentferner
Proposed coating structure:	steel: priming coat: WSA 1000-20 with 50 - 60 µm dry film thickness finishing coat: *WAY 2000-40 with 50 - 60 µm dry film thickness

Special notes:

*Further Mipa topcoats are available. Please contact your technical adviser or our application technicians.

For professional use only.

The details of the paragraphs - Proposed coating structure, Characteristics, Theoretical spreading rate, VOC - refer to the colour shade RAL 7035. For other colour shades, these may deviate.

Paints that have been tinted with aluminium pastes must be protected from heat. Store at max. 35 °C. Failure to take this into account may lead to an internal pressure build-up.

Drying times reduce with increasing air velocity and degreasing relative humidity. When drying with air guns, the drying time can be reduced considerably. Optimum processing conditions: air temperature 20 - 25 °C, object temperature > 15 °C, relative air humidity 40 - 60 %, air velocity > 0,4 m/s.

Cleaning of tools:

Clean tools immediately after use with Mipa WBS-Pistolenreiniger.