

## Product Information

Mipa 2K-Clear coat C 128 with UV protection can be applied without adding thinner. Excellent gloss and stability of the paint is assured even by one coat application. Therefore an important economy of material and processing time is obtained. It is ready to use after the addition of the suitable amount of Mipa 2K-Härter MS 10 or Mipa 2K-Härter MS 25. Excellent resistance to all environmental and climatic circumstances, yellowing resistant and durable gloss.  
Consumption: 6 - 8 m<sup>2</sup> / l.

Colour shade	transparent			
Mixing ratio	2 : 1 by volume			
Hardener	Mipa 2K - Härter MS 10 or MS 25			
Thinners	Apply without dilution!			
Spraying viscosity 20°C	16 - 18 s 4 mm DIN			
Application	spraying pressure	spraying nozzle	spraying operations	
Air / Flowjar - Spray gun	4 - 5 bar	1,4 mm	1 - 2	
Airless / Airmix				
Pot life	4 - 6 h			
Coat thickness / dry film	40 - 50 µm			
Curing time / Flash off time	5 - 10 min. between the spraying operations			
Dry	recoat time	dust dry	set to touch	full hardness
Object temp. 20°C		30 min.	12 h	24 h
Object temp. 60°C		5 min.	30 min.	2 h

**Operation conditions:** from + 10 °C and up to 75% relative air humidity .

**Storage:** if stored tightly closed, in original packaging, Mipa 2K-Klarlack C 128 has a shelf-life of at least 3 years.

Marking	VbF	Hazardous materials ordinance
Mipa 2K-Klarlack C 128	A II	flammable, Xn contains xylene
Mipa 2K-MS-Härter	A II	flammable, Xi contains aliphatic polyisocyanate

All products should be disposed of in relation to the regulations of the environmental health authorities. Protect your Environment!

This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacture of our products. However the data is not binding and without warranty.