

Summary of Mipa Hardeners for the correct use in

Mipa 2K-Primers and 2K-Fillers

2K-Primers / 2K-Fillers	Mipa 2K-Härter MS 40 extra lang	Mipa 2K-Härter MS 25 normal	Mipa 2K-Härter MS 10 kurz	Mipa 2K-Härter H 10 kurz	Mipa 2K-Härter H 5 extra kurz	Mipa 2K-Härter HS 25 normal	Mipa 2K-Härter HS 10 kurz	Mipa 2K-Härter HS 5 extra kurz
Mipa 2K-Transparent Sealer			by vol. 2 : 1					
Mipa 2K-HS-Filler F41							by vol. 4 : 1	by vol. 4 : 1
Mipa 4+1 Acrylfiller HS				by vol. 4 : 1	by vol. 4 : 1			
Mipa 2K-HS-Fillprimer				by vol. 4 : 1	by vol. 4 : 1	by vol. 4 : 1		
Mipa 2K-Acrylgrund				by vol. 7 : 1	by vol. 7 : 1	by vol. 7 : 1		
Mipa 2K-Acryl-Grundierfiller				by weight 10 : 1				
Mipa 2K-HS-Directfiller F31							by vol. 3 : 1	by vol. 3 : 1
Mipa 2K - Primer AZ				by vol. 4 : 1	by vol. 4 : 1		by vol. 4 : 1	

This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacture of our products. However the data is not binding and without warranty.

Summary of Mipa Hardeners for the correct use in

Mipa 2K-Primers and 2K-Fillers

2K-Primers / 2K-Fillers	Mipa Härter WPZ	Mipa Härter PS	Mipa Härter P	Mipa WBS EP-Härter	Mipa EP-Härter E 10 kurz	Mipa EP-Härter E 25 normal			
Mipa Aktivprimer	by vol. 2 : 1								
Mipa 2K-Primer CF	by vol. 2 : 1								
Mipa WBS EP-Grundierfiller				by vol. 4 : 1					
Mipa EP- Grundierfiller					by vol. 2 : 1	by vol. 2 : 1			
Mipa P 60 S		by vol. 98 : 2							
Mipa 2K-Polyester Spachtel			by vol. 100:2						

This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacture of our products. However the data is not binding and without warranty.

Marking	VbF	Hazardous materials ordinance
Mipa 2K-Härter HS 5 extra kurz	A II	inflammable, Xi irritant
Mipa 2K-Härter HS10 kurz	A II	inflammable, Xi irritant
Mipa 2K-Härter HS 25 normal	A II	inflammable, Xi irritant
Mipa 2K-Härter H 5 extra kurz	A II	inflammable, Xi irritant
Mipa 2K-Härter H 10 kurz	A II	inflammable, Xi irritant
Mipa 2K-Härter MS 10 kurz	A II	inflammable, Xi irritant
Mipa 2K-Härter MS 25 normal	A II	inflammable, Xi irritant
Mipa 2K-Härter MS 40 extra lang	A II	inflammable, Xi irritant
Mipa Härter WPZ	A I	highly inflammable, Xn harmful to health contains 4-Methyl-pentan-2-on
Mipa Härter PS	A III	oxidizing, C caustic contains Cyclohexanon, peroxide
Mipa Härter P	n/at	oxidizing, Xi irritant contains Dibenzoyl peroxide
Mipa WBS EP-Härter	n/a	Xi irritant, contains 1,3-Benzol dimethan amine
Mipa EP-Härter E 10 kurz	A II	inflammable, Xn harmful to health contains xylene, 4-Methyl-pentan-2-on
Mipa EP-Härter E 25 normal	n/a	inflammable, Xn harmful to health contains 4,4'-Isopropylidendiphenol-1-chloro- 2,3-epoxypropan-Cooligomeren, xylene

All above listed hardeners, excluding Mipa EP-Härter, Mipa WBS EP-Härter, Mipa Härter WPZ, Mipa Härter PS and Mipa Härter P, contain aliphatic polyisocyanates.