

## **Mipalin Synthetic topcoat**

## The universal classic with long-term warranty

**Mipalin** the classic synthetic topcoat for simple and high-quality finishes.

- fast drying
- highly scratch and impact resistant
- weather and yellowing resistant
- excellent gloss and flow













MIPA SE · Am Oberen Moos 1 · D-84051 Essenbach · Tel.: +498703/922-0 · Fax: +498703/922-100 mipa@mipa-paints.com · www.mipa-paints.com

# Mipalin - The true classic

**Mipalin** is a high-quality topcoat based on synthetic resin. It is especially adapted to coat easily machines, agricultural vehicles and large vehicles.

### Das Mipalin synthetic resin range

Mipalin KH-Kunstharz- Decklack	Available as ready-mixed topcoat in 120 colours and in 11 or 5 I contai- ner, including many RAL and agricultural engine colours. More than 10 000 colours can be created additionally by the mixing system. Also unusual colours as well as other qualities and glosses can be produced quickly in appropriate quantities.
Mipalin FG-Spezial- Chassislack	Particularly resistant special high-build paint for high-quality chassis coatings. Six standard colours available, individual colours can be created by means of mixing system.
Mipa Härterverdünnung	Can be added instead of thinner Mipa Verdünnung UN or UN 21, leads to fast drying and high surface hardness
Mipa Grundierungen	Quality already starts with substrate pre-treatment. Mipa Primer, Mipa Grundierfiller BZ and other high-quality 1K and 2K primer provide an optimal solution for all kind of substrates. Fast drying, high resistance and excellent overcoatability are guaranteed.



#### spray viscosity air: 18-22 sec. (1

air: 18-22 sec. (10-20% thinner) airless: 40-50 sec. (without thinner)



spray applicationairnozzle:1,3-1,5mmpressure:4-5 barnumber of coats:2

*airless* 0,28 mm 120-150 bar 1 ½-2



drying at 20°C dust dry: 30-60 min. set to touch: 6-8 hours completely cured: 24 hours



technical data sheets

Mipalin Kunstharz-Decklack Mipa FG-Spezial-Chassislack Mipa Härterverdünnung



MIPA SE · Am Oberen Moos 1 · D-84051 Essenbach · Tel.: +498703/922-0 · Fax: +498703/922-100 mipa@mipa-paints.com · www.mipa-paints.com