



SPRITZKABINENKLEBELACK "ANTIDUST"

MP Spritzkabinenklebelack "AntiDust" is an aqueous solution of resins and tackifiers for application to spray booths walls by brush or spray. The product has a very pale colour, after application it is clear and colourless. No drying time. The film does not completely dry out at ambient temperature and has a tacky surface which collects and holds dust to help keeping the spray booth area free of airborne particles. When the coating is contaminated with dust or overspray, it can easily be washed off with water and a pressure washer. A new coat MP Spritzkabinenklebelack "AntiDust" can then be applied.

METHOD OF USE:

Use as supplied.

By spray: use a spray gun with a fluid tip of 70 thou (1,8 mm). Apply by a single pass using a fairly wide fan. Take care that sufficient coverage is achieved and a continuous coating is applied – no bare patches.

By paint brush or paste brush: apply a thin coat only, to avoid runs.

By roller: a single coat is adequate. Wash out equipment with water.

REMOVAL:

MP Spritzkabinenklebelack "AntiDust" is easily removed from booth walls by washing with water, it is very easily soluble. A discrete mist of paint overspray on the booth wall will not cause any problem to wash away the MP Spritzkabinenklebelack "AntiDust" film to obtain a clean wall. When paint overspray forms a complete paint film on the booth wall the water cannot access the tacky coating underneath and it will be more difficult to wash it away. In these cases it helps to make small cuts in the paint film surface to help water penetration.

MP Spritzkabinenklebelack "AntiDust" is suitable for application to most factory finished paint spray booths of either 2 pack polyurethane, 2 pack epoxy, or other stove converted paint. In spray bake booths with temperatures above 40 degrees C the coating will eventually dry out making paint overspray difficult to remove. The coating will remain effective for up to 50 hrs at low bake temperatures and should be washed down in time (check regularly) and re-applied.

COVERAGE:

Approx. 8-10 m²/litre. After the water has evaporated away the tacky coating should be 1–2 thou (0,02-0,04 mm) thick.

PRECAUTIONS:

MP Spritzkabinenklebelack "AntiDust" is not suitable for use on uncured paints such as cellulose or household paints, as the coating could react with the paint film. Tacky Surface Coating is not suitable for use on steel or galvanised booth walls because repeated washing with water as part of the booth maintenance procedure can cause corrosion (rust and white rust).