

Mipa Premium-Klarlack-Spray

Item no 21501 + gloss level

Technical data sheet

page 1 / 2

Intended use

Mipa Premium-Klarlack-Spray is a premium quality clearcoat with excellent flow and excellent anti-sagging properties. This fast drying clearcoat stands out due to its very good filling properties and gloss level. Mipa Premium-Klarlack-Spray is suitable as a non-yellowing protective coating with outstanding UV-resistance. Resistant to all climatic conditions, scratch, and shock resistant.

Processing instructions



Substrates

Mipa water- and solvent-based basecoats, cured and sanded old paintworks.

Pre-treatment / cleansing

Please refer to the section "Substrate preparation" for detailed information.

Characteristics

Very good weather resistance, lightfast, non-yellowing
Very high scratch and shock resistance
High surface hardness with good elasticity at the same time
Good flow, high gloss
Good polishability

Colour / gloss level

Colourless high gloss (0020) / colourless satin matt (0023) / colourless matt (0027)




Preparation

Before use, shake can vigorously for 1 - 2 minutes!



Application

Spray to test - spray distance approx. 20 - 30 cm
2 - 3 coats, dry film thickness: 40 - 50 µm




Flash-off time

3 - 5 min between coats



After use

After use, turn can upside down and spray until the valve is clean, this prevents the valve from clogging up.



Drying time at 20 °C

Dust dry after approx.	5 - 10 min
Set to touch after approx.	20 - 30 min
Ready for assembly after approx.	2 h

Processing conditions From +10 °C and up to 80 % relative air humidity. Ensure adequate air ventilation.

Storage Can be stored for 2 years in cool and dry places.

VOC-regulation EU limit value for this product (cat. B/e): 840 g/l
This product contains max. 700 g/l of VOC.

Safety information See safety data sheet

Substrate preparation:

Remove old coatings that have not cured or are not sound.

Do not use on thermoplastic substrates.

Intact, sound old paintworks, factory paintings:

1. Pre-clean with Mipa Silikonentferner.
2. Then sand with P 400 - 500.
3. Afterwards, degrease with Mipa Silikonentferner.

Mipa Basecoats:

Observe the respective Technical data sheet of the Mipa basecoat system!