

# Mipa WBS PC-Primer-Spray

Item no 213380000

Technical data sheet

**mipa**

Professional Coating Systems

page 1 / 2

## Intended use

Mipa WBS PC-Primer-Spray is a colourless adhesion promoter that is especially suited for polycarbonate substrates such as headlight lenses. Due to the water-based formulation, Mipa WBS PC-Primer does not dissolve the sensitive polycarbonate substrates and in due course, ensures an unproblematic and gentle recoating of the plastic. By overrecoating with Mipa 2K clearcoats, high-quality headlight repairs can be achieved.

## Processing instructions



### Substrates

Adhesion promoter for following plastic substrates:  
Polycarbonate plastics, POM, PU, ABS, PVC and PA

### Pre-treatment / cleansing

Pre-clean with Mipa WBS Reiniger Final.

Caution: Cleaners containing solvents must not be used under any circumstances, as this would corrode the PC plastic.

Please refer to the section "Substrate preparation" for detailed information.

### Characteristics

Excellent adhesion  
Gentle on plastics  
Colourless

### Colour / gloss level

colourless




### Preparation

Before use, shake can vigorously for 1 - 2 min!



### Application

Spray to test - spray distance approx. 20 - 30 cm  
2 - 3 thin coats, dry film thickness: 5 - 10 µm



### Flash-off times

2 - 3 min between coats



### After use

After use, turn can upside down and spray until the valve is clean, this prevents the valve from clogging up.

Version: en 0322

This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.

MIPA SE · Am Oberen Moos 1 · D-84051 Essenbach · Tel.: +49(0)87 03/922-0 · Fax: +49(0)87 03/922-100 · mipa@mipa-paints.com · www.mipa-paints.com



## Drying time at 20 °C

Dust dry after approx. 5 - 10 min

Overcoatable after approx. 35 - 45 min

**Processing conditions** From +10 °C and up to 80 % relative humidity. Ensure adequate air ventilation.

**Storage** Can be stored for 1 year in cool and dry places.

**VOC-regulation** EU limit value for the product (cat. B/e): 840 g/l  
This product contains max. 700 g/l of VOC.

**Safety information** See safety data sheet

## Processing instructions

Do not overcoat with polyester-based materials.

Mipa WBS PC-Primer can also be used as an adhesion promoter on POM, PU, ABS, PVC and PA plastics.

If these types of plastic are sensitive to solvents due to their design (e.g. very thin-walled components) or the composition of the plastic, the plastic-protecting character of Mipa WBS PC-Primer will also be an advantage for these materials.

Subsequent overcoating with solvent-based or water-based topcoats is possible without any problems.

## Substrate preparation:

### Plastic substrates:

1. Before painting, reheat the object to be painted for 60 minutes at 60°C.
2. Degrease with Mipa Kunststoffreiniger antistatisch or Mipa Silikonentferner.
3. Sand thoroughly with MP Softpad Superfine using Mipa Kunststoffreiniger antistatisch or Mipa Silikonentferner .
4. Clean again with Mipa Kunststoffreiniger antistatisch or Mipa Silikonentferner.
5. Allow parts to dry completely.
6. Recommended for neutralising electrostatic charges:

Blow off the surfaces by means of MP Ionisierungspistole X-ION that cleans and neutralises in one operation, which reduces dust inclusions when coating. In addition, this avoids differences in pigment orientation when overcoating with metallic/ effect basecoats.

ATTENTION: Releasing agents must be removed completely!

After the previously mentioned preparation, we recommend doing a wetting test with water. If the water drops roll off quickly, repeat the pre-treatment.

Due to the wide range of plastic types and compounds available on the market, preliminary tests on original parts are indispensable.