

Miparox Anti-Rost-Spray is an epoxy-resin based anti-corrosion protective coating which forms a dark grey almost black protective layer which also acts as a primer. Once fully cured (12 - 24 hours) the rust is neutralised and the surface can be re-coated.



#### **Substrate:**

Remove loose rust, dirt and grease.  
Suitable for sheet metal, ferrous metal, steel.



#### **Pretreatment / Cleansing**

Pre-cleansing using Mipa Silikonentferner

#### **Characteristics:**

Rust is neutralised and chemically converted ferrous metal turn black.  
Combats corrosion suitable for the effective treatment of rust.  
Long-term protection against corrosion and primer in one operation.  
Durable protective coating.  
Can be overcoated with polyester-based materials after a drying time for 24 hours at room temperature.

<b>Colour / Grade of Gloss:</b>	Transparent	
<b>Preparation:</b>		Shake can vigorously until the mixing balls move freely!
<b>Application:</b>		Spray to test. Spraying distance approx. 20 - 25 cm 3 - 4 coat - allowing the product to dry in between each coating.
<b>Flash-off:</b>		3 - 5 min. between each coating
<b>After use:</b>		Turn can upside down and spray until the valve is clean, this prevents the valve from clogging up.
<b>Drying Times:</b>		
<b>Drying:</b>	<b>Set to touch:</b>	12 - 24 h
	<b>Re-coatable:</b>	24 h
	<b>Re-coatable with polyester materials:</b>	24 h
<b>Processing Conditions:</b>	From +15°C and up to 65% relative air humidity	
<b>Storage:</b>	In tightly closed original containers at least 2 years shelf life	
<b>VOC- Regulation:</b>	EC limiting value for the product (cat. B/e): 840 g/l (2007) This product contains a maximum of 800 g/l VOC [ 6.68 lbs/gal]	
<b>Safety Information:</b>	Read the corresponding Material Safety Data Sheet	

Dieses Merkblatt dient der Information! Die Angaben entsprechen nach unserer Kenntnis dem Stand der Technik und beruhen auf langjährigen Erfahrungen bei der Herstellung unserer Produkte. Die Angaben erfolgen jedoch unverbindlich und ohne Gewähr.