


**Intended use**

High-quality waterborne glossy 2K polyurethane paint that provides particularly high resistance to chemical agents and UV. Especially suitable for coatings on vehicles, metal facades as well as machines and constructions exposed to high strain. Its very slow initial drying and the related very good spray mist absorption render the product perfect for application on large surfaces.

**Processing instructions****Mixing ratio****hardener**

WPU 9425-25

**by weight (lacquer : hardener)**

4 : 1

**by volume (lacquer : hardener)**

4 : 1

**Hardener**

Mipa WPU 9425-25 WBS 2K PUR Hardener

**Pot life**

3,5 h at 20 °C\*

**Thinner**

Mipa WBS VE-Wasser

**Processing viscosity**

Always stir first the hardener in the paint and then thin by adding Mipa WBS VE-Wasser. Never mix water with the hardener.

**gravity spray gun**

—

**Airmix/Airless**

—

**Application mode****application mode****hardener****pressure  
(bar)****nozzle  
(mm)****spray  
passes****dilution**gravity spray gun/  
HVLP

—

2,0 - 2,5

1,2 - 1,3

2

20 - 25 %

Airmix / Airless  
compound pressure

—

1,0 - 2,0  
100 - 120

0,23 - 0,28

1 - 2

0 - 10 %

**Drying time****hardener****object  
temperature****dust dry****set to  
touch****ready for  
assembly****sandable****recoatable**

—

20 °C

1 - 1,5 h

8 - 10 h

24 h

—

—

—

60 °C

—

1,5 h

1,5 h

—

—

Fully cured after 7 - 8 days (at 20 °C).

**Note**

<b>Characteristics:</b>	binder base: polyurethane polyester system solids content (% by weight): ~ 51 solids content (% by volume): ~ 34 delivery viscosity DIN 53211 4 mm (in s): thixotropic density DIN EN ISO 2811 (kg/l): ~ 1,4 gloss level ISO 2813 at 60° (GU): 50 - 60 semi-gloss
<b>Properties:</b>	High water resistance Highly UV- and weather-resistant Highly resistant to solvents Scratch-resistant Excellent resistance to chemical and mechanical strains Heat resistance: - Short-term heat exposure: 180 °C - Permanent heat exposure: 150 °C
<b>Theoretical spreading rate:</b>	~ 27,5 m²/kg for 10 µm dry film thickness. ~ 30,6 m²/l for 10 µm dry film thickness.
<b>Storage:</b>	For at least 2 years in the unopened original container. Optimum storage conditions between + 5 °C and + 25 °C, avoid direct sunlight. Other storage conditions may lead to undesirable properties of the material.
<b>VOC:</b>	< 60 g/l. **
<b>Processing conditions:</b>	From + 10 °C and up to 70 % relative humidity. Ensure adequate air ventilation.
<b>Substrate preparation:</b>	Remove oil, grease, rust, mill scale, rolling skins, as well as other substances impairing the function of the coating!  Attention: A direct adhesion cannot be taken as granted due to most different kinds of metals, alloys, metallic and conversion coatings and so on. The adhesion must therefore be tested on the original substrate.  Steel: - Blast to cleaning degree Sa 2½, remove blast residues and overcoat promptly. - D-rust with hand and power tools to degree of cleanliness St 3. - Degrease with Mipa WBS Reiniger or Mipa Silikonentferner.  Zincd substrates: - Clean the surface with the ammonia solution Mipa Zinkreiniger. - Sweep blast.  Aluminium: - Degrease with Mipa 2K-Verdünnung, sand thoroughly with sandpaper P 360/400 and clean subsequently with Mipa Silikonentferner.
<b>Proposed coating structure:</b>	Steel, zincd substrates: Priming coat: ***WEP 1000-20 with 60 - 80 µm dry film thickness. Finishing coat: WPU 2425-50 with 50 - 60 µm dry film thickness.  Aluminium: Priming coat: ***WEP 1000-20 with 25 - 30 µm dry film thickness Finishing coat: WPU 2425-50 with 50 - 60 µm dry film thickness

**Special notes:**

\*Attention: The end of pot life does not manifest itself by viscosity increase. Exceeding the pot life results in a lower resistance to mechanical and chemical strains, in a reduction of gloss and in a higher tendency to blister.

\*\*This product contains the following maximum VOC-values:  
- Applied by spraying with hardener WPU 9425-25: < 210 g/l of VOC.

\*\*\*Further Mipa primers are available. Please contact your technical adviser or our application technicians.

For professional use only.

The details of the paragraphs - Proposed coating structure, Characteristics, Theoretical spreading rate, VOC - refer to the colour shade RAL 7035. For other colour shades, these may deviate.

Paints that have been tinted with aluminium pastes must be protected from heat. Store at max. 35 °C. Failure to take this into account may lead to an internal pressure build-up.

Drying times reduce with increasing air velocity and degreasing relative humidity. When drying with air guns, the drying time can be reduced considerably. Optimum processing conditions: air temperature 20 - 25 °C, object temperature > 15 °C, relative air humidity 40 - 60 %, air velocity > 0,4 m/s.

Check colour shade prior to application.

Especially UV-resistant pigmentations (e.g. pastel shades for facades) are available on demand.

**Cleaning of tools:**

Clean tools immediately after use with Mipa WBS-Pistolenreiniger.

If required we also offer cleaning agents that are suitable for 2-component mixing and dosing units. Please contact your technical adviser or our application technicians.